



	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
<b>PRODUCT DESCRIPTION</b>				
Surface treatment	-	-	-	<b>Protectsol</b> <sup>TRIPLE ACTION</sup>
Surface Complex	-	-	-	<b>D-Max+</b>
Foam	-	-	-	<b>CXP HD</b>
Thickness	EN 428	-	mm	<b>6.2 mm</b>
Weight	EN 430	-	kg/m <sup>2</sup>	4,2
Length	EN 426	-	lm	20.5 Standard
Width	EN 426	-	lm	1,5
Impact Protection Index	AC- P90-205	-	%	<b>IPI = 52%</b>
<b>SPORT PROPERTIES</b>				
Shock absorption	EN 14808	≥ 25	%	P1
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 2
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 à 65	cm	-
	ITF	-	-	-
<b>TECHNICAL CHARACTERISTICS</b>				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.25
<b>CLASSIFICATION</b>				
Fire	EN 13501-1	-	-	Cir-s1
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99% inhibits growth
<b>DECLARATION OF PERFORMANCE</b>				
	DOP n°xxx	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	METHODE D'INSTALLATION		
	Recommandation GERFLOR	Unité	Résultat
Glued installation: "Original"	Level of dampness of the subfloor	%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolsport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% humidity (CCM)

**COLOUR RANGE**



**8840 Wood Black**



**4331 Wood Natural**



**3708 Wood Grey**



**4453 Wood Blue**



**4506 Wood Green**



**8068 Wood Chocolate**

TARAFLEX™ MULTI-USE 6.2



(3) The implementation of an effective cleaning method is the best defence against infection